



HAIPHONG PAINT JOINT STOCK COMPANY

Head office : 12 Lach Tray St., Ngo Quyen dist., Haiphong City
 Manufacture : No. 21, 208 Street, An Dong - An Duong - Hai Phong
 Tel : 84-31.3835710-3593681 Fax : 84-31.3571053-3593680
 Website : www.sonhaiphong.com.vn



ISO 9001
 ISO 14001
 BUREAU VERITAS
 Certification



No. 8030
 12 - 2015

ALKYPHOENIX S36 - 70HV

DESCRIPTION

ALKYPHOENIX S36-70HV is a short oil alkyd based on mix vegetable oil having high viscosity used for wood coatings

PERFORMANCE

- Good gloss & gloss retention
- Flow properties
- Fast cure
- Good hardness
- Good adhesion

SUGGESTED USES:

Acid curing for base & top coat wood finishes.

STORE AND HANDING

To ensure maximum stability and optimum resin properties, resin should be stored in closed containers at temperature below 30°C and away from heat sources and sunlight. All storage should conform to local fire and building codes. Drums should be stored away from all sources of flame or combustion. Keep container closed when not in use.

STANDARD PACKING

Resin is supplied in a 200 kgs net metal drum.

Specifications

Appearance	Clear & clean
Color (Gardner)	Max 4
Acid Value (mg KOH / g solids)	Max 10
Viscosity, 25 ⁰ C, Gardner (50% in Xylene)	Y - Z (1,500- 2,500 cps)
Solvent type	Xylene
Solid content (%)	70 ± 1
OH value	136 ± 2

Composition

Oil content (%)	36
Phthalic Anhydric (%)	42

Typical properties

Specific Gravity at 25°C	0.95 - 1.1
-----------------------------	------------

Solubility

- Mineral Spirit	Partially dilutable
- Xylene	dilutable
- Toluene	dilutable
- Solvesso 100	dilutable
- Solvesso 150	dilutable
- Ethyl acetate	dilutable
- Butyl Acetate	dilutable
- MIBK	dilutable
- Ethyl alcohol	indilutable
- Butyl alcohol	Partially dilutable